Amendments to the Claims:

The following listing of claims will replace all prior versions, and listings, of claims in the application:

- 1. (Original) A non-crosslinked flame-retardant resin composition comprising:
- (A) a non-crosslinked base resin which contains

 a propylene resin containing 50 wt% or more of propylene monomer, and

 a thermoplastic resin of which a melting point is 180°C or more,
- (B) a metallic hydrate;
- (C) a hindered phenolic antioxidant;
- (D) a sulfurous antioxidant; and
- (E) a metallic oxide.
- 2. (Original) The non-crosslinked flame-retardant resin composition according to claim 1, wherein (A) the non-crosslinked base resin contains the propylene resin by 40-90 wt% and the thermoplastic resin of which a melting point is 180°C or more by 60-10 wt%.
- 3. (Currently Amended) The non-crosslinked flame-retardant resin composition according to claim 1-or 2, wherein the thermoplastic resin of which a melting point is 180°C or more is polymethylpentene.

- 4. (Currently Amended) The non-crosslinked flame-retardant resin composition according to any one of claims 1 to 3 claim 1, wherein 100 part weight of (A) the non-crosslinked base resin contains:
 - 30-250 part weight of (B) the metallic hydrate;
 - 0.3-15 part weight of (C) the hindered phenolic antioxidant;
 - 0.3-30 part weight of (D) the sulfurous antioxidant; and
 - 0.3-30 part weight of (E) the metallic oxide.
- 5. (Currently Amended) The non-crosslinked flame-retardant resin composition according to any one of claims 1 to 4 claim 1, wherein (D) the sulfurous antioxidant is an imidazole compound.
- 6. (Currently Amended) The non-crosslinked flame-retardant resin composition according to any one of claims 1 to 5 claim 1, wherein (E) the metallic oxide is an oxide of at least one metal selected from zinc (Zn), aluminum (Al), magnesium (Mg), lead (Pb) and tin (Sn).
- 7. (Currently Amended) The non-crosslinked flame-retardant resin composition according to any one of claims 1 to 6 claim 1, wherein (B) the metallic hydrate is one of magnesium hydroxide and aluminum hydroxide.
- 8. (Currently Amended) A non-halogenous insulated wire comprising a conductor covered with the non-crosslinked flame-retardant resin composition according to any one of claims 1 to 7 claim 1.

9. (Original) A wiring harness comprising:

one of a single wire bundle including only the non-halogenous insulated wires according to claim 8, and a mixed wire bundle including at least the non-halogenous insulated wires according to claim 8 and vinyl chloride insulated wires; and

a wiring-harness protective material for covering the wire bundle, in which one of a non-halogenous resin composition, a vinyl chloride resin composition, and a halogenous resin composition other than the vinyl chloride resin composition is used as a base material.